

OBJECT CARPET

Typical characteristics EN 1307

Name of article:	Silver/Gold Loop 1800
Method of production ISO 2424:	tufted
Width ISO 3018:	ca. 400 cm
Surface structure ISO 2424:	Brilliance loop
Colourways ISO 2424:	uni
Pile material:	100% Polyamid Antron® Lumena
Primary backing ISO 2424:	PP / PA
Secondary backing ISO 2424:	conductive latexation and action back
Overall weight ISO 8543:	ca. 3.000 g/m ²
Overall thickness ISO 1765:	ca. 8,0 mm
Mass of effective pile ISO 8543:	ca. 1.530 g/m ²
Pile service weight:	ca. 1.740 g/m ²
Effective pile thickness ISO 1766:	ca. 6,8 mm
Pile density ISO 8543:	ca. 0,226 g/cm ³
Stitch rate ISO 1763:	ca. 237.900/m ²

Application

Wearability:	32
Comfort class:	LC 5

Physical features as to the building

Electrostatic loading:	< 2 KV														
Surface resistivity:	10 ⁹ Ω														
Sound absorption:	+ 29 dB														
Acoustical absorption α _w	0.25														
Sound absorption α _s	<table><thead><tr><th>Hz</th><th>125</th><th>250</th><th>500</th><th>1000</th><th>2000</th><th>4000</th></tr></thead><tbody><tr><td>α_s</td><td>0,03</td><td>0,08</td><td>0,27</td><td>0,28</td><td>0,40</td><td>0,46</td></tr></tbody></table>	Hz	125	250	500	1000	2000	4000	α _s	0,03	0,08	0,27	0,28	0,40	0,46
Hz	125	250	500	1000	2000	4000									
α _s	0,03	0,08	0,27	0,28	0,40	0,46									
Transparency to heat:	ca. 0,11 K*m ² /W														
Flammability EN 13 501 – 1:	Cfl- s1 (alt B1)														

Ecological characteristics

DIBt-AgBB Schema	AbZ.: Z-156.601-734
Conformity certificate	0988-CPD-0410
PRODIS / GUT - ID	Lizenz-Nr.: BBDCFB63
EPD (Environmental Product Declaration)	EPD-GUT-2009311-D

Fastness

Light fastness	≥ 5
Water fastness	≥ 4
Friction fastness	≥ 3-4

01/2012 Subject to production technical changes

