

# OBJECT CARPET

## Typical characteristics EN 1307

Name of article:	<b>Flash 1400</b>
Method of production ISO 2424:	tufted
Width ISO 3018:	ca. 400 cm
Surface structure ISO 2424:	
Colourways ISO 2424:	tricoloured
Pile material:	100% Polyamid Antron® Brilliance®
Primary backing ISO 2424:	PP
Secondary backing ISO 2424:	conductive latexation and action back
Overall weight ISO 8543:	ca. 3.000 g/m <sup>2</sup>
Overall thickness ISO 1765:	ca. 17,0 mm
Mass of effective pile ISO 8543:	ca. 1.080 g/m <sup>2</sup>
Pile service weight:	ca. 1.440 g/m <sup>2</sup>
Effective pile thickness ISO 1766:	ca. 15,0 mm
Pile density ISO 8543:	ca. 0,10 g/cm <sup>3</sup>
Stitch rate ISO 1763:	ca. 21.000 /m <sup>2</sup>

## Application

Wearability:	32
Comfort class:	LC 5

## Physical features as to the building

Electrostatic loading:	< 2 KV														
Surface resistivity:	10 <sup>9</sup> Ω														
Sound absorption:	+ 30 dB														
Acoustical absorption $\alpha_w$	0.35														
Sound absorption $\alpha_s$	<table><thead><tr><th>Hz</th><th>125</th><th>250</th><th>500</th><th>1000</th><th>2000</th><th>4000</th></tr></thead><tbody><tr><td><math>\alpha_s</math></td><td>0,03</td><td>0,09</td><td>0,,3</td><td>0,35</td><td>0,37</td><td>0,52</td></tr></tbody></table>	Hz	125	250	500	1000	2000	4000	$\alpha_s$	0,03	0,09	0,,3	0,35	0,37	0,52
Hz	125	250	500	1000	2000	4000									
$\alpha_s$	0,03	0,09	0,,3	0,35	0,37	0,52									
Transparency to heat:	ca. 0,15 K*m <sup>2</sup> /W														
Flammability EN 13 501 – 1:	Cfl- s1 (alt B1)														

## Ecological characteristics

DIBt-AgBB Schema	AbZ.: Z-156.601-26
Conformity certificate	1658-CPD-1219
PRODIS / GUT - ID	Lizenz-Nr.: 0D6BED54
EPD (Environmental Product Declaration)	EPD-GUT-2009311-D

## Fastness

Light fastness	≥ 5
Water fastness	≥ 4
Friction fastness	≥ 3-4

01/2012 Subject to production technical changes

