

OBJECT CARPET

Typical characteristics EN 1307

Name of article:

Method of production ISO 2424:

Width ISO 3018:

Surface structure ISO 2424:

Colourways ISO 2424:

Pile material:

Primary backing ISO 2424:

Secondary backing ISO 2424:

Overall weight ISO 8543:

Overall thickness ISO 1765:

Mass of effective pile ISO 8543:

Pile service weight:

Effective pile thickness ISO 1766:

Pile density ISO 8543:

Stitch rate ISO 1763:

SL Glory 1500

tufted

SL Fliesen / Tiles / Dalles 48 x 48 cm

Brilliance frisé

uni

100% Polyamid Antron®

PES

conductive latexation, bitumen-heavy backing with glass fibre reinforcement and PP fleece covering

ca. 5.000 g/m²

ca. 10,0 mm

ca. 1300 g/m²

ca. 1.500 g/m²

ca. 6,0 mm

ca. 0,21 g/cm³

ca. 130.200/ m²

Application

Wearability:

32

Comfort class:

LC 5

Physical features as to the building

Electrostatic loading:

< 2 KV

Surface resistivity:

10⁹Ω

Sound absorption:

+ 25 dB

Acoustical absorption α_w

0,30

Sound absorption α_s

Hz	125	250	500	1000	2000	4000
α_s	0,00	0,05	0,10	0,25	0,50	0,65

Transparency to heat:

ca. 0,11 K*m²/W

Flammability EN 13 501 – 1:

Cfl- s1 (alt B1)

Ecological characteristics

DIBt-AgBB Schema

AbZ.: Z-156.601-551

Conformity certificate

1658-CPD-1221

PRODIS / GUT - ID

EPD (Environmental Product Declaration)

EPD-GUT-209411-D

Fastness

Light fastness

≥ 5

Water fastness

≥ 4

Friction fastness

≥ 3-4

01/2012 Subject to production technical changes

